



Overview

This is a copper nickel alloy with good resistance to bio-fouling, galling and impingement.

Typical Applications

Typical applications include couplings, valves, fasteners and pumps.

Chemical Analysis

Typical analysis:

	Al	Mn	Si	Cr	Ni	Cu	Fe	-
Min	1.0	3.5	-	-	13.5	-	0.7	%
Max	2.0	5.5	-	0.5	16.5	BAL	1.2	%

Mechanical Properties

Typical properties in the annealed condition:

Tensile MPA min	Yield (0.2% offset), MPA Min	Elongation in 2" or 4D min%
725	430	18

All material we supply has full traceability with inspection certification in accordance with BS EN 10402 3.1. We can supply material with intent of BS EN 10402 3.2 inspection certification on request.

We have onsite PCN and SNT Level II inspectors who can test material to your requirements.

All information included in this sheet is intended as a guide only and is correct to the best of our knowledge.